

AMENDMENTS TO THE CLAIMS

1. (Original) An optical laminate (optical laminate C) which comprises a layer (layer A) comprising a resin having a negative intrinsic birefringence and at least one layer (layer B) comprising a transparent resin, having substantially no orientation and laminated at least on one face of layer A and satisfies a relation $|Re(A)| > |Re(B)|$, wherein $Re(A)$ and $Re(B)$ represent an in-plane retardation of layer A and an in-plane retardation of layer B, respectively, measured with light having a wavelength of 400 to 700 nm.
2. (Original) The optical laminate according to Claim 1, wherein $|Re(B)|$ is 20 nm or smaller.
3. (Currently amended) The optical laminate according to Claim 1 ~~Claims 1 and 2~~, which satisfies a relation $Tg(A) > Tg(B) + 20$, wherein $Tg(A)$ and $Tg(B)$ represent glass transition temperatures in °C of the resin of layer A and the resin of layer B, respectively.
4. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 3~~, which satisfies a relation $Re(450) > Re(550) > Re(650)$, wherein $Re(450)$, $Re(550)$ and $Re(650)$ represent in-plane retardations at wavelengths of 450 nm, 550 nm and 650 nm, respectively.
5. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 4~~, which satisfies a relation $\Sigma n_z > \Sigma n_y - 0.002$, wherein Σn_z represents a refractive index in a direction of a thickness and Σn_y and Σn_x represent refractive indices in two directions which are perpendicular to the direction of a thickness and perpendicular to each other of optical laminate

C measured with light having a wavelength of 550 nm, and Σn_x , Σn_y and Σn_z satisfy relations $\Sigma n_x < \Sigma n_y$ and $\Sigma n_x < \Sigma n_z$.

6. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 5~~, wherein an unevenness in a thickness of layer A is 3.0% or smaller of an average thickness of layer A.

7. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 6~~, wherein the resin having a negative intrinsic birefringence is a resin selected from a group consisting of vinyl aromatic polymers, polyacrylonitrile polymers and polymethyl methacrylate polymers.

8. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 7~~, wherein the resin having a negative intrinsic birefringence is a vinyl aromatic polymer.

9. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 8~~, wherein the resin having a negative intrinsic birefringence is a resin selected from a group consisting of polystyrene and copolymers of styrene and maleic anhydride.

10. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 9~~, wherein the transparent resin is a resin having an alicyclic structure.

11. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 10~~, wherein the transparent resin is a norbornene polymer.

12. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 11~~, wherein the transparent resin is a hydrogenation product of a ring-opening polymer of a norbornene monomer or a hydrogenation product of a ring-opening copolymer of a norbornene monomer.

13. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 12~~, wherein the transparent resin has a tensile elongation at break of 30% or greater.

14. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 13~~, wherein the layer comprising a transparent resin and having substantially no orientation (layer B) is laminated on both faces of the layer comprising a resin having a negative intrinsic birefringence (layer A).

15. (CURRENTLY AMENDED) The optical laminate according to Claim 1 ~~any one of Claims 1 to 14~~, wherein an adhesive layer is disposed between the layer comprising a resin having a negative intrinsic birefringence (layer A) and the layer comprising a transparent resin and having substantially no orientation (layer B).

16. (Currently amended) The optical laminate according to Claim 1 ~~any one of Claims 1 to 15~~,

which satisfies relations $T_g(A) > T_g(D)$ and $T_g(B) > T_g(D)$, wherein $T_g(D)$ represents a glass transition temperature or a softening point in °C of an adhesive in the adhesive layer.

17. (Currently amended) An optical element comprising a laminate of the optical laminate described in Claim 1 ~~any one of Claims 1 to 16~~ and a polarizer plate.

18. (Currently amended) A liquid crystal display device which uses at least one sheet of the optical laminate described in Claim 1 ~~any one of Claims 1 to 16~~.

19. (Currently amended) The liquid crystal display device according to Claim 18, wherein said liquid crystal display device comprises a liquid crystal cell of ~~a mode of the liquid crystal is an~~ in-plane switching (IPS) mode.